


# Technical Data Sheet

## Corkcomfort Glue-down Sanded

Dimensions Available 600x300x4 mm - 23-5/8x11-13/16x5/32 inches

Domestic	EN ISO 10874:2012	Class	23 (a)	
----------	-------------------	-------	--------	---

Commercial	EN ISO 10874:2012	Class	31 (b)	
------------	-------------------	-------	--------	---

General properties - EN 12104	Standard - Test Method	Unit	Specification
-------------------------------	------------------------	------	---------------

Dimensions	EN 427	mm	≤ 0,2% up to 1,0 mm max.
------------	--------	----	--------------------------

Overall thickness	EN 428	mm	0; +0,25
-------------------	--------	----	----------

Squareness and Straightness: ≤ 400mm > 400mm	EN 427	mm	≤ 0,5 ≤ 1,0
--	--------	----	----------------

Apparent density	EN 672	Kg/m <sup>3</sup>	≥ 95% of nominal value (450)
------------------	--------	-------------------	------------------------------

Dimensional stability	EN 434	%	≤ 0,4
-----------------------	--------	---	-------

Curling after exposure to heat	EN 434	mm	≤ 6
--------------------------------	--------	----	-----

Moisture content	EN 12105	%	2,5 - 6
------------------	----------	---	---------

Classification properties - EN 12104			
--------------------------------------	--	--	--

Residual indentation	EN 433	mm	≤ 0,40
----------------------	--------	----	--------

Safety properties - EN 14041			
------------------------------	--	--	--

Formaldehyde emission	DIN EN 717-1	Class	E1
-----------------------	--------------	-------	----

Electrical behaviour	EN 1815	KV	Not Antistatic
----------------------	---------	----	----------------

Content pentachlorophenol (PCP)	CEN/TR 14823 (hd-W 409)	mg/Kg	PCP free
---------------------------------	-------------------------	-------	----------

Optional properties			
---------------------	--	--	--

Thermal resistance	EN 12667	m <sup>2</sup> K/W	R ≤ 0,150
--------------------	----------	--------------------	-----------

Impact sound reduction	ISO 140-8	dB (ΔL <sub>w</sub> )	12
------------------------	-----------	-----------------------	----

Step sound	NF S 31 - 074	dB (L <sub>n,e,w</sub> )	65
------------	---------------	--------------------------	----

(a) Must be varnished on-site with minimum 3 coats of w-700 or w-2000 or another recommended varnish

(b) Must be varnished on-site with minimum 3 coats of w-2000 or another recommended varnish for this level of use (see recommendation table in the packaging)

[www.wicanders.com](http://www.wicanders.com)

