

FLOORLEUM FREE FLOORLEUM with antistatic property. A good solution in wide range of industrial projects.

| Specification | overall thickness | 2.0mm | width x length | 1820mm x 18m |
|---|---|-------------------------|----------------|--------------|
| JIS Registered No. | No. GB0506143 (JIS A 5705 Vinyl Sheet Flooring) | | | |
| | | | | |
| Packing | 18m/roll | | | |
| Net Weight | 101.5kg/roll | | | |
| Recommended Applications | factories (semiconductor or electronic devices) / offices / hospitals | | | |
| Recommended Adhesive from TOLI | dried mortar and concrete | Epo Gray ST , US Cement | | |
| | humid mortar and concrete | Epo Gray S | | |
| Welding | Welding rod for heat-welding is available on a color-by-color basis. | | | |
| Notes on Installation | | | | |
| Recommended Maintenance Wax from TOLI | "ELEX" from C×S Corporation (Antistatic) | | | |

Custom Order If you ask for a different thickness, please contact TOLI sales rep.

> ◆Due to the antistatic chemical inside the product, sometimes the surface might become sticky. Please clean the floor on a regular basis.

- ◆The dirt and stains will be more visible on the floor covering with lighter plain colors, compared to dark colors. Also they are more likely to stick with the deep-embossed surface than the flat surface.
- ◆Please be aware that some rubber casters might cause color-contamination.
- ◆Please note that the product has the indigenous odor from its materials.
- ♦Where you have to keep the dust away (e.g. clean rooms), do not apply the wax. ♦Please bear in mind that the antistatic performance might differ according to the kind of sub-floor.



Others

|| TS331





TS332







MADE IN JAPAN





▲ TS333

Antistatic Property <in accordance with JIS A 1454>

| | Surface (Ω) | Volume (Ω) |
|-------------------|------------------------|------------------------|
| 2.0mm vinyl sheet | 1.4 x 10 ¹¹ | 3.5 x 10 ¹⁰ |
| FLOORLEUM FREE | 3.4 x 10 ⁸ | 2.7 x 10 ⁷ |

◆ Antistatic Property to Human Bodies <in accordance with JIS L 1021-16>

| | Rubber Shoes (kv) |
|-------------------|-------------------|
| 2.0mm vinyl sheet | over3.0 |
| FLOORLEUM FREE | 0.52 |

☆ This is the test result at 23 degrees centigrade, 25%RH. Please bear in mind that antistatic property may differ due to the sub-floor.